



Technical Data Sheet

Bondloc B2007 Aqua Epoxy Stick

PRODUCT DESCRIPTION

B2007 is a hand-mixable, specialty epoxy putty for repairs to damp, wet areas and underwater surfaces. After mixing, it forms a polymer compound that may be applied underwater (either fresh or salt water) and will bond tenaciously to substrates such as fiberglass, concrete, ceramic, glass, metal, wood, and many plastics. Each stick contains pre-measured portions of base and activator throughout — no measuring or mixing tools are necessary. The consistency (like modeling clay) eliminates drips and runs, facilitates adhesion to the substrate, and allows the material to be shaped and formed as needed before curing begins. After 60 minutes the application can be drilled, sawed, sanded, carved, and painted. B2007 cures to an off-white colour. Suitable for interior or exterior use it is resistant to chemicals, water, and temperature extremes. B2007 contains no solvents or VOCs. It is non-flammable and releases no noxious fumes. It won't shrink or pull away. The unused portion stays fresh for future use when saved in its original package.

APPLICATIONS

B2007 can be used to patch dings, holes, gouges, repair decks and hulls, pools hot tubs and spas, marine recreational equipment, leaking gaskets, gutters and tanks. B2007 will bond fiberglass, metal, wood, concrete, glass and many plastics. B2007 works on wet, damp, dry surfaces and underwater.

USEFUL HINTS/NOTES

Mixing: Twist or cut off required amount. To mix, knead with fingers to a uniform colour. If mixing is difficult, warm B2007 to room temperature or slightly above. Apply to the surface to be repaired (within 2 minutes of mixing). The mixed epoxy does not exhibit high bond strength at this point, but appears to be merely lying on the surface. Force into any cracks or holes to be filled and strike off excess material, preferably with a tool wetted with clean water. Work the material forcefully into the surface and apply pressure until adhesion begins to take effect. For a smooth appearance of the cured compound, hand rub with water or a damp cloth prior to hardening. Remove excess material before hardening begins. After 15-20 minutes the epoxy will harden like metal and start to form a tenacious bond. After just 45 minutes B2007 is completely cured and can be drilled, sawed, carved, sanded, stained or painted.

INSTRUCTIONS FOR USE

In order to achieve optimum adhesion, surface should be cleaned free of grease or dirt. Scuffing or sanding the surface prior to cleaning helps to ensure a good bond.

TECHNICAL FEATURES

Resin	Off White
Chemical Resistance	Hydrocarbons, Ketones, esters, halo-carbons, alcohols, aqueous salt solutions, diute acids and bases
Electrical Resistance	30,000 mega Ohms
Dielectric Strength (Steel)	300 Volts/mil
Shrinkage	<1%
Non Volatile Content	100%
Shelf Life	24 months @ 24°C

CURED PERFORMANCE

Initial Cure	1 hour
Full Cure Time	24 hours
Lap Shear Strength (Steel)	6.2 MPa
Shore D Hardness	65
Compressive Strength	1.9gm/cm ³

PROPERTIES

Opening Time	5 mins
Max Temp Resistance	121°C Continuous 149°C Intermittent

STORAGE

Store in cool conditions, preferably away from direct sunlight or excessive heat. Shelf life at least 24 months @ 24°C.

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

PACKAGING FORMAT

Tubes.....50g, 114g
Clam.....50g

Bondloc UK Ltd.
Units 1 & 2
Bewdley Business Park
Bewdley, Worcestershire
DY12 2TZ, UK

+44 (0) 1299 269 269
sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

